



# LIQUID RUBBER OVERVIEW

		A:B MIX RATIO	POT LIFE (MINUTES)	MIXED VISCOSITY CPS	Demold Time	SHORE A HARDNESS	Color	CU. IN./LB.	TEAR STRENGTH PLI	ELONGATION AT BREAK %
POLYURETHANE RUBBER	ReoFlex™ 20	1:1	30	1,800	16 HOURS	20	OFF-WHITE	26.7	50	1,000
	ReoFlex™ 30	1:1	30	1,800	16 HOURS	30	OFF-WHITE	27.7	55	1,000
	ReoFlex™ 40	1:1	25	1,200	16 HOURS	40	OFF-WHITE	27.2	60	1,000
	ReoFlex™ 50	1:1	30	1,400	16 HOURS	50	OFF-WHITE	26.7	80	500
	ReoFlex™ 60	1:1	30	1,800	16 HOURS	60	OFF-WHITE	26.7	125	581
	VytaFlex™ 10	1:1	30	800	16 HOURS	10	CLEAR AMBER	27.9	30	1,000
	VytaFlex™ 20	1:1	30	1,000	16 HOURS	20	CLEAR AMBER	27.7	35	1,000
	VytaFlex™ 30	1:1	30	1,800	16 HOURS	30	OFF-WHITE	27.3	68	1,000
	VytaFlex™ 40	1:1	30	2,000	16 HOURS	40	OFF-WHITE	26.9	60	660
	VytaFlex™ 50	1:1	60	2,000	16 HOURS	50	OFF-WHITE	26.7	80	400
	VytaFlex™ 60	1:1	60	2,000	16 HOURS	60	OFF-WHITE	26.6	136	480
	PMC™ -121/30 Wet or Dry	1:1	30	1,800	16 HOURS	30	CLEAR AMBER	27.7	82	1,000
	PMC™ -121/50 Wet	1:1	30	1,400	16 HOURS	50	CLEAR AMBER	26.7	85	500
	PMC™ -724	1:10	20	VARIABLE	16 HOURS	40	CLEAR AMBER	VARIABLE	90	90
	PMC™ -726	1:10	25	3,000	16 HOURS	60	CLEAR AMBER	20.4	100	400
	PMC™ -744	2:1	15	3,400	16 HOURS	44	CLEAR AMBER	27.5	90	400
	PMC™ -746	2:1	15	1,200	16 HOURS	60	CLEAR AMBER	26.9	100	650
	PMC™ -780 Wet or Dry	2:1	30	2,000	16 HOURS	80	CLEAR AMBER	27.2	200	700
	PMC™ -790	2:1	20	3,000	16 HOURS	90	CLEAR AMBER	25.9	300	600
	Brush-On™ 40	1:1	20	BRUSHABLE	16 HOURS	40	OFF-WHITE	23.6	60	1,000
Brush-On™ 50	1:1	30	BRUSHABLE	16 HOURS	50	OFF-WHITE	27.0	80	400	
Brush-On™ 60	1:1	30	BRUSHABLE	16 HOURS	60	OFF-WHITE	19.0	80	400	
EZ-Spray™ 45	1:1	20	SPRAYABLE	16 HOURS	50	BLUE	27.0	80	400	
TIN SILICONES	Mold Max™ 10	100:10*	45	15,000	24 HOURS	10	LIGHT PINK	24.1	90	375
	Mold Max™ 20	100:10*	90	20,000	24 HOURS	20	LIGHT PINK	23.1	60	450
	Mold Max™ 30	100:10*	60	30,000	24 HOURS	30	PINK	23.4	125	400
	Mold Max™ 40	100:10*	45	35,000	24 HOURS	40	MINT GREEN	23.5	100	225
	OOMOO™ 25	1:1	10	4,250	75 MINUTES	25	BLUE	20.6	40	250
	OOMOO™ 30	1:1	30	4,250	6 HOURS	30	LAVENDER	20.6	40	250
	PoYo Putty™ 30	1:4	5	PUTTY	30 MINUTES	30	LIGHT PINK	22	90	300
	PoYo Putty™ 40	1:4	5	PUTTY	30 MINUTES	40	LIGHT PINK	22	90	300
PLATINUM SILICONES	SORTA-Clear™ 40	100:10*	60	35,000	16 HOURS	40	TRANSLUCENT	27.8	120	400
	Smooth-Sil™ 910	100:10*	20	7,000	6 HOURS	10	OFF-WHITE	24.0	50	450
	Smooth-Sil™ 920	1:1	30	20,000	4 HOURS	20	TRANSLUCENT	23.5	100	400
	Smooth-Sil™ 930	100:10*	45	40,000	24 HOURS	30	BLUE	24.0	110	400
	Smooth-Sil™ 940	100:10*	20	35,000	24 HOURS	40	PINK	23.4	100	300
	Smooth-Sil™ 950	100:10*	45	35,000	24 HOURS	50	BLUE	22.3	155	320
	Dragon Skin™ Q	1:1	8	23,000	75 MINUTES	10	TRANSLUCENT	25.8	100	1000
	Dragon Skin™	1:1	20	23,000	5 HOURS	10	TRANSLUCENT	25.8	100	1000
	Rebound™ 25	1:1	20	BRUSHABLE	6 HOURS	25	ORANGE	23.6	102	690
	Ecoflex™ 00-30	1:1	45	7,000	4 HOURS	00-30	TRANSLUCENT	26	55	900
	Ecoflex™ 00-40	1:1	45	3,000	4 HOURS	00-40	TRANSLUCENT	26	38	900
	Ecoflex™ 5	1:1	1	13,000	5 MINUTES	5	TRANSLUCENT	25.8	75	1,000
	Body Double™	1:1	5	BRUSHABLE	30 MINUTES	25	PURPLE	23.7	100	500
	Body Double™ Fast Set	1:1	90 SEC	BRUSHABLE	5 MINUTES	25	GREEN	23.7	100	500
	Equinox™ 25	1:1	1	PUTTY	7 MINUTES	25	BLUE	21.5	120	400
	Equinox™ 35	1:1	1	PUTTY	7 MINUTES	35	LIGHT PURPLE	21.3	140	430
Equinox™ 50	1:1	1	PUTTY	7 MINUTES	50	YELLOW	21.3	165	300	
EZ-Spray™ Silicone 35	1:1	1.5	17,000	15 MINUTES	35	Purple	24.1	100	415	
POLY-SULFIDES	FMC™ 200	100:12*	60	14,000	16 HOURS	20	BLACK	20.5	N/A	700
	FMC™ 201	100:12*	60	12,000	16 HOURS	15	BLACK	20.5	N/A	950
	FMC™ 205	100:12*	100	7,000	16 HOURS	15	BLACK	21.0	N/A	1000

\* Rubbers Measured by Weight

\*\* Rubbers Can Be Pigmented Using So-Strong™ (urethanes) or Silc Pig™ (silicones) Colorants